

TIMBER PROPERTIES

The purpose of this document is to provide additional information to the builder and tradies about the types of timber that they are working with. With this document made readily available, they can determine the timber specifications codes that are on VUETRADE™ product's technical data sheet and hence using the product in compliance to the Australian Standards.

Index No.	Standard trade name	Joint group	
		Unseasoned (J Group)	Seasoned (JD group)
8	Alder, rose	J4	JD4
22	Ash, alpine	J3	JD3
30	Ash, mountain	J3	JD3
37	Ash, silvertop	J2	JD2
84	Blackbutt	J2	JD2
86	Blackbutt, New England	J2	JD2
87	Blackbutt, W.A.	J2	JD2
121	Box, brush	J2	JD2
127	Box, grey, coast	J1	JD1
150	Box, yellow	J1	JD1
165	Brownbarrel	J3	JD3
178	Candlebark	J3	JD3
114	Fir, Douglas	J4	JD4
253	Gum, blue, southern	J2	JD2
254	Gum, blue, Sydney	J2	JD2
266	Gum, grey	J1	JD1
267	Gum, grey, mountain	J2	JD2
269	Gum, manna	J3	JD2
272	Gum, mountain	J3	JD3
279	Gum, red, forest	J1	JD1
281	Gum, red, river	J2	JD2
284	Gum, rose	J2	JD2
289	Gum, shining	J3	JD3
293	Gum, spotted	J1	JD1
310	Hardwood, Johnstone River	J1	JD1
139*	Hemlock	J4	JD4
322	Ironbark, grey	J1	JD1
325	Ironbark, red	J1	JD1
326	Ironbark, red, broad-leaved	J1	JD1
327	Ironbark, red, narrow-leaved	J1	JD1
341	Jarrah	J2	JD2
154*	Kapur	J2	JD2
344	Karri	J2	JD2

Continued next page...

NOTE: All VUETRADE™ products are compliant with the requirements of AS1720 and AS4600

Page 1 of 2

TIMBER PROPERTIES

Index No.	Standard trade name	Joint group	
		Unseasoned (J Group)	Seasoned (JD group)
169*	Keruing	J2	JD2
173*	Kwila(merbau)	J2	JD2
384	Mahogany, red	J1	JD1
387	Mahogany, southern	J2	JD2
391	Mahogany white	J1	JD2
432	Marri	J2	JD2
221*	Meranti, dark red	J4	JD3
434	Messmate	J3	JD3
477	Oak, silky, northern	J4	JD4
486	Oak, tulip, brown	J2	JD2
488	Oak, tulip, red	J2	JD2
505	Penda, red	J1	JD1
512	Peppermint, narrow-leaved	J3	JD2
533	Pine, Carribean	J3	JD4
544	(pine) Cypress, white	J3	JD3
545	Pine, hoop	J4	JD4
551	Pine, loblolly	J3	JD3
554	Pine, maritime	J4	JD4
559	Pine, radiata	J4	JD4
561	Pine, slash	J3	JD3
615	Satinash, Eungella white	J3	JD3
618	Satinash, grey	J3	JD3
620	Satinash, Kuranda	J2	JD3
635	Satinay	J2	JD2
668	Stringybark, Blackdown	J1	JD1
671	Stringybark, brown	J2	JD2
676	Stringybark, red	J2	JD2
677	Stringybark, silvertop	J3	JD2
680	Stringybark, white	J2	JD2
681	Stringybark, yellow	J2	JD2
688	Tallowwood	J1	JD2
723	Turpentine	J2	JD2
746	Walnut, yellow	J3	JD4
747	Wandoo	J1	JD1

NOTE:

1. Timber joints that are comprised of two or more different species, the joint group allocated to that joint shall be that appropriate to the weakest material in that joint (ie. If a joint comprise of J1 and J2, design capacity will be based on J2 in technical data sheet)
2. Timber properties and their joint group are taken from AS 1720.2: Timber Properties and AS1684.2: Non-cyclonic Areas.
3. Number in Joint Group indicates the strength of the timber where 1 being the strongest and 4 being the weakest.

NOTE: All VUETRADE™ products are compliant with the requirements of AS1720 and AS4600

Page 2 of 2